

## AMENDMENTS TO THE CLAIMS

1. (Previously Presented) An apparatus comprising:
  - a first metal electrode layer;
  - a metal nitride layer adjacent to the first metal electrode layer wherein the metal nitride layer comprises an excess of holes in the metal nitride layer and wherein the metal nitride layer is one of (a) doped with hafnium or (b) deposited in the presence of excess nitrogen;
  - a polymer ferroelectric layer adjacent to the metal nitride layer;
  - a metal oxide layer adjacent to the polymer ferroelectric layer; and
  - a second metal electrode layer adjacent to the metal oxide layer.
2. (Original) The apparatus of claim 1 wherein the first metal electrode layer and second metal electrode layer are tantalum.
3. (Original) The apparatus of claim 1 wherein the polymer ferroelectric layer is polyvinylidene fluoride.
4. (Original) The apparatus of claim 1 wherein the polymer ferroelectric layer is a polyvinylidene fluoride trifluoroethylene copolymer.
5. (Original) The apparatus of claim 1 wherein the metal nitride layer is tantalum nitride.
6. (Canceled)
7. (Previously Presented) The apparatus of claim 5 wherein the tantalum nitride has a hole density of approximately between  $10^{20}/\text{cm}^3$  and  $10^{21}/\text{cm}^3$ .
8. (Canceled)
9. (Previously Presented) The apparatus of claim 5 wherein the tantalum nitride has a hole density of approximately between  $1.8 \times 10^{21}/\text{cm}^3$  and  $5.4 \times 10^{21}/\text{cm}^3$ .

10. (Original) The apparatus of claim 1 wherein the metal oxide layer is tantalum oxide.
11. (Original) The apparatus of claim 10 wherein the tantalum oxide layer is doped with hafnium to create excess holes in the tantalum oxide lattice.
12. (Original) The apparatus of claim 11 wherein the tantalum oxide has a hole density is approximately between  $10^{20}/\text{cm}^3$  and  $10^{21}/\text{cm}^3$ .
13. (Original) The apparatus of claim 10 wherein the tantalum oxide layer is deposited in the presence of excess oxygen to create excess holes in the tantalum oxide lattice.
14. (Original) The apparatus of claim 13 wherein the tantalum oxide has a hole density of approximately between  $7 \cdot 10^{21}/\text{cm}^3$  and  $2.1 \cdot 10^{22}/\text{cm}^3$ .
- 15-28. (Canceled)
29. (Previously Presented) An apparatus comprising:  
a metal nitride layer, wherein the metal nitride layer comprises an excess of electron traps in the metal nitride layer and wherein the metal nitride layer is one of (a) doped with hafnium or (b) deposited in the presence of excess nitrogen;  
a polymer ferroelectric layer adjacent to the metal nitride layer; and  
a metal oxide layer adjacent to the polymer ferroelectric layer.
30. (Original) The apparatus of claim 29 wherein the polymer ferroelectric layer is polyvinylidene fluoride.
31. (Original) The apparatus of claim 29 wherein the polymer ferroelectric layer is a polyvinylidene fluoride trifluoroethylene copolymer.
32. (Original) The apparatus of claim 29 wherein the metal nitride layer is tantalum nitride.

33. (Canceled)
34. (Canceled)
35. (Original) The apparatus of claim 29 wherein the metal oxide layer is tantalum oxide.
36. (Original) The apparatus of claim 35 wherein the tantalum oxide layer is doped with hafnium to create electron traps in the tantalum oxide lattice.
37. (Original) The apparatus of claim 35 wherein the tantalum oxide layer is deposited in the presence of excess oxygen to create electron traps in the tantalum oxide lattice.
- 38-46. (Canceled)
47. (Previously Presented) An apparatus comprising:  
a first metal electrode layer;  
a metal nitride layer adjacent to the first metal electrode layer wherein the metal nitride layer comprises an excess of holes in the metal nitride layer;  
a polymer ferroelectric layer adjacent to the metal nitride layer;  
a tantalum oxide layer adjacent to the polymer ferroelectric layer, wherein the tantalum oxide layer is doped with hafnium to create excess holes in the tantalum oxide lattice; and  
a second metal electrode layer adjacent to the metal oxide layer.
48. (Previously Presented) An apparatus comprising:  
a first metal electrode layer;  
a metal nitride layer adjacent to the first metal electrode layer wherein the metal nitride layer comprises an excess of holes in the metal nitride layer;  
a polymer ferroelectric layer adjacent to the metal nitride layer;  
a tantalum oxide layer adjacent to the polymer ferroelectric layer, wherein the tantalum oxide layer is doped with hafnium to create excess holes in the tantalum oxide lattice and has a hole density between  $10^{20}/\text{cm}^3$  and  $10^{21}/\text{cm}^3$ ; and  
a second metal electrode layer adjacent to the metal oxide layer.

49. (Previously Presented) An apparatus comprising:
- a metal nitride layer, wherein the metal nitride layer comprises an excess of electron traps in the metal nitride layer;
  - a polymer ferroelectric layer adjacent to the metal nitride layer; and
  - a tantalum oxide layer adjacent to the polymer ferroelectric layer, wherein the tantalum oxide layer is doped with hafnium to create excess holes in the tantalum oxide lattice.